

Compilation of our raw materials – alumina crucible

	AL₂O₃ C 799
Composition	Al ₂ O ₃ : 99,7 %
Density	3,90 g/cm ³
Open porosity	0,0 %
Flexural strength	300 Mpa
Thermal expansion coefficient	7,8 K ⁻¹
Thermal shock resistance	175 K
Max. operational temperature	1800 °C