

## Compilation of our raw materials - Porcelain

|   | <b>Porcelain C 110</b> |
|---|------------------------|
| Density   | 2,34 g/cm <sup>3</sup> |
| Flexural strength   | 80 Mpa                 |
| Dielectric strength                                       | 20 kV/mm               |
| Dielectric loss factor<br>20 °C 1 Mhz (10 <sup>-3</sup> ) | 12,0                   |
| Specific resistance<br>20 °C                              | 10 <sup>11</sup> Ωm    |