

Compilation of our raw materials - Porcelain

	Porcelain C 110	Porcelain C 120
Density	2,34 g/cm ³	2,58 g/cm ³
Flexural strength	80 Mpa	140 Mpa
Dielectric strength	20 kV/mm	20 kV/mm
Dielectric loss factor 20 °C 1 Mhz (10 ⁻³)	12,0	12,0
Specific resistance 20 °C	10 ¹¹ Ωm	10 ¹¹ Ωm