

Compilation of our raw materials - Steatite

	Steatite C 221
Density	2,83 g/cm ³
Flexural strength	160 Mpa
Dielectric strength	20 kV/mm
Dielectric loss factor 20 °C 1 Mhz (10 ⁻³)	1,2
Specific resistance 20 °C	10 ¹¹ Ωm