

## Compilation of our raw materials – Tumbling mills

	<b>porcelain C 110</b>	<b>porcelain C 130</b>
Density	2,34 g/cm <sup>3</sup>	2,6 g/cm <sup>3</sup>
Flexural strength	80 Mpa	140 Mpa
Dielectric strength	20 kV/mm	20 kV/mm
Dielectric loss factor 20 °C 1 Mhz (10 <sup>-3</sup> )	12,0	15,0
Specific resistance 20 °C	10 <sup>11</sup> Ωm	10 <sup>11</sup> Ωm